

Prime Sports Floor Chemical Resistance Chart

<u>Chemical</u>	<u>1 Hour</u>	<u>Chemical</u>	<u>1 Hour</u>
Ammonia	0	Laundry Detergent	0
Bleach	0	Sodium hydroxide, NaOH (5%)	0
Disinfectant	0	Human Perspiration	0
Isopropyl Alcohol	0		

Categories

- * SD: Surface dulling; Indicates that the specimen suffered from a loss of gloss
- * CC: Color change; Indicates that the specimen suffered discoloration or bleaching, or both
- * SA: Surface attack; Indicates that the specimen suffered surface damage such as softening, warping, swelling, blistering, peeling, raised or rough area

Subjective category ratings

- 0 = no change
- 1 = slight change
- 2 = moderate change
- 3 = severe change

** Tested in accordance with ASTM F 925; chemicals exposed to tile surface for one hour and examined within 5 minutes of removal